

**SALES & SERVICE  
IN YOUR STATE  
PH: 1300 658 007**



# Megasealed™

Megasealed Bathrooms Aust. Pty Ltd ABN: 84 074 726 757  
Megasealed Insulation Aust. Pty Ltd ABN: 84 138 909 985

## MEGAFLEX SPECIFICATIONS

### ANTI – FUNGUS SILICONE

Quality Characteristics	Unit	Specification	Test Method
1. * Appearance (Characteristic)	-	Paste	Visual
2. * Appearance (Colour)	-	Clear, White, etc.	Visual
3. * Tack Free Time at 23 °C	Minute	15 maximum	JIS A 1439
4.* Slump at 23 °C	mm	3 maximum	JIS A 1439
5.* Extrusion Rate at 23 °C	g	30-80	§ I
6. * Hardness; Type A	-	15-30	JIS K 6249
7. * Tensile Strength	MPa	1.0 minimum	JIS K 6249
8. * Elongation at break	%	400 minimum	JIS K 6249
9.* Tensile Shearing Adhesive Strength (aluminium / aluminium)	MPa	0.5 minimum	JIS K 6249
10.* Designation Failure (%CF)	%	80-100	JIS K 6249

Curing Condition: 23 ± 2 °C, Humidity 50 ± 5 % - 7 days

**[megasealed.com.au](http://megasealed.com.au)**

**NEW SOUTH WALES**  
**Sydney Head Office**  
Unit 5, 133 Beauchamp Road  
Postal: PO Box 195  
Matraville NSW 2036  
Tel: 1300 658 007  
Fax: 02 9289 3655  
[nsw@megasealed.com.au](mailto:nsw@megasealed.com.au)

**ACT**  
**Canberra**  
Unit 3, 94 Bayldon Road  
Queanbeyan NSW 2620  
Tel: 1300 658 007  
Fax: 02 6262 6100  
[act@megasealed.com.au](mailto:act@megasealed.com.au)

**QUEENSLAND**  
**Brisbane**  
Unit 1, 37 Mortimer Road  
Acacia Ridge QLD 4110  
Tel: 1300 658 007  
Fax: 07 3216 6526  
[qld@megasealed.com.au](mailto:qld@megasealed.com.au)

**SOUTH AUSTRALIA**  
**Adelaide**  
3/900 South Road  
Edwardstown SA 5039  
Tel: 1300 658 007  
Fax: 08 8371 3500  
[sa@megasealed.com.au](mailto:sa@megasealed.com.au)

**VICTORIA**  
**Melbourne**  
346 Darebin Road  
Fairfield VIC 3078  
Tel: 03 9499 1766  
Fax: 03 9499 3977  
[vic@megasealed.com.au](mailto:vic@megasealed.com.au)

**WESTERN AUSTRALIA**  
**Perth**  
2/71 Truganina Road  
Malaga WA 6090  
Tel: 1300 658 007  
Fax: 08 9248 2700  
[wa@megasealed.com.au](mailto:wa@megasealed.com.au)